

Case Consulting Laboratories, Inc.

622 Route Ten
Whippany, New Jersey 07981
Tel. 973-428-9666
Fax. 973-887-4419
E-Mail: case@case-labs.com

April 22, 2005

To: VEXCON Chemicals, Inc.
7240 State Road
Philadelphia, PA 19135

Attention: Darryl Manuel

From: Charles Anthony

Project No's.: 6312, 6320 and 6331

Subject: Coefficient of Friction Determinations

INTRODUCTION

We were authorized to determine the coefficient of friction of samples identified below in accordance with ASTM D 2047 utilizing the James Machine fitted with leather sole material. The samples were tested in triplicate.

RESULTS

Uncoated

Coefficient of Friction (Average Over 4 Cycles)			Coefficient of Friction (Average Over 12 Cycles)
Replicate 1	Replicate 2	Replicate 3	
0.80	0.80	0.76	0.78

Certi-Shine Clear

Coefficient of Friction (Average Over 4 Cycles)			Coefficient of Friction (Average Over 12 Cycles)
Replicate 1	Replicate 2	Replicate 3	
0.55	0.55	0.50	0.54

Certi-Shine Finish Coat

Coefficient of Friction (Average Over 4 Cycles)			Coefficient of Friction (Average Over 12 Cycles)
Replicate 1	Replicate 2	Replicate 3	
0.67	0.63	0.60	0.63

Darryl Manuel
VEXCON Chemicals, Inc.

April 22, 2005
Page Two

DISCUSSION

A coefficient of friction value of 0.5 or greater is generally accepted for classifying a walking surface as slip resistant.

Respectfully submitted,

Charles Anthony
President

CASE CONSULTING LABORATORIES, INC.

ra