



VEXCON
CHEMICALS, INC.

Concrete solutions for architects, engineers and builders since 1974
888-839-2661 | sales@vexcon.com | 7240 State Road | Philadelphia, PA 19135 vexcon.com

POWERSEAL STAIN GUARD **STAIN RESISTANCE CHART**

<u>CHEMICAL</u>	<u>RESULTS</u>
Aluminum Chloride	NE
Ammonium Chloride	NE
Anti Freeze	NE
Aviation Gasoline's	NE
Battery Acid 30% Sulfuric Acid	M
Brake Fluid	NE
Carbonic Acid 85%	NE
Chromic Acid 10%	NE
Cooking Oil	NE
Ethyl Alcohol (Beer)	NE
Gasoline	NE
Grease	NE
HCL (10%)	NE
Iodine	NE
Isopropyl Alcohol	NE
Jet Fuel	NE
Ketchup	NE
Lemon Juice – Citric Acid	NE
Milk	NE
Motor Oil	NE
Mustard	NE
NAOH (10%)	NE
Orange Juice – Citric Acid	NE
Phosphoric Acid 85%	NE
Potassium Dichromate	NE
Red Wine	NE
Salt Spray Resistance	500 hr
Sodium Sulfate	NE
Sodium Sulfite	NE
Tannic Acid	NE
Transmission Fluid	NE
Urine	NE
Vinegar Acetic Acid (10%)	NE
Zinc Sulfate	NE

- * **S = Stain**
- * **NE = No effect**
- * **SS = Slight stain**
- * **M = Minimal**

The resistance is based upon proper application to saturation on treated surface. Results can differ where applications are compromised.