

Test Data

Product Overview

Submittal Year: 2018
NTPEP Number: CCC-2018-02-003
Manufacturer Name: Vexcon Chemicals, Inc.
Product Name: Certi-Vex Envio Cure Clear 500

Test Data [Summary](#)

Release Status: **Restricted**

Additional Documentation

Report Title	Document
--------------	----------

Currently no reports are available.

AASHTO M 148 - Visual Inspection

	Unit	Result
Color		Clear
Consistency (Acceptable/Unacceptable)		OK
Condition of film at 7 days (Acceptable/Unacceptable)		OK
Deleterious Reaction with Concrete (Yes/No)		None
Drying Time Test	Hrs:Mins	2:00

AASHTO T 155 - Testing Parameters

	Unit	Testing Parameters
Method of application		Spray
Rate of application	l/m ²	0.2

AASHTO T 155 - Physical Testing

	Unit	Rep1	Rep2	Rep3	Average
Density	kg/m ³				1009
Moisture Loss @ 24 Hours	kg/m ²	0.15	0.21	0.27	0.21
Moisture Loss @ 72 Hours	kg/m ²	0.28	0.38	0.47	0.38
Reflectance Test (ASTM E 1347) [using CIE D65/2°]					
Long-Term Settling Test (MNDOT Test Procedure (72 hrs))	ml				
Nonvolatile Content Test (ASTM D 1644)	%	17.77	18.38	18.09	18.08
Flash Point Test (ASTM D 93)	F				>212

FTIR Spectrum

Document

[NTPEP CCC-2018-02-003.pdf](#)

Attached Documents

Document Type	Documents
Technical Literature	CC105 Certi-Vex Envio Cure Clear - DS.pdf
SDS	CC105 Certi-Vex Envio Cure - CLEAR -SDS (GHS).pdf
Product Certification with Manufacturers Specification	Certificate of Quality - Certi-Vex Envio Cure Clear 500.pdf
IR Scan	Certi-Vex Envio Cure Clear 500 IR Scan.pdf
Install Instructions	CC105 Certi-Vex Envio Cure 500 (GHS) - Label.pdf

Test Data

Product Overview

Submittal Year: 2018
NTPEP Number: CCC-2018-02-003
Manufacturer Name: Vexcon Chemicals, Inc.
Product Name: Certi-Vex Envio Cure Clear 500

Test Data

Summary

AASHTO M 148 - Visual Inspection

	Unit	Result
Color		Clear
Consistency (Acceptable/Unacceptable)		OK
Condition of film at 7 days (Acceptable/Unacceptable)		OK
Deleterious Reaction with Concrete (Yes/No)		None
Drying Time Test	Hrs:Mins	2:00

AASHTO T 155 - Testing Parameters

	Unit	Testing Parameters
Method of application		Spray
Rate of application	l/m ²	0.2


AASHTO T 155 - Physical Testing

	Unit	Rep1	Rep2	Rep3	Average
Density	kg/m ³				1009
Moisture Loss @ 24 Hours	kg/m ²	0.15	0.21	0.27	0.21
Moisture Loss @ 72 Hours	kg/m ²	0.28	0.38	0.47	0.38
Reflectance Test (ASTM E 1347) [using CIE D65/2°]					
Long-Term Settling Test (MNDOT Test Procedure (72 hrs))	ml				
Nonvolatile Content Test (ASTM D 1644)	%	17.77	18.38	18.09	18.08
Flash Point Test (ASTM D 93)	F				>212

Infrared Document

DOCUMENT

[NTPEP CCC-2018-02-003.pdf](#)



NTPTP CCC-2018-02-003
Vexcon Chemicals, Inc
Certi-Vex Envio Cure Clear 500